



## Typical Properties

### ***PU11092***

*85°A unfilled general purpose cast elastomer suitable for industrial environments*

<b>Property</b>	<b>Test Method</b>	<b>Value</b>	<b>SI Units</b>	<b>Value</b>	<b>Imp Units</b>
Color	-	Blaze Orange	-	-	-
Shore Hardness	Shore A	85 °	A	85 °	A
Tensile Strength	ASTM D412	26	MPa	3770	lbf/in <sup>2</sup>
Elongation @ Break	ASTM D412	490	%	490	%
Nicked Crescent Tear Strength	ASTM D624	78	N/mm	442	lb/in

Author S. Kotrulja Issue No 00

Approved By S. Kotrulja Date of Approval/Issue 8 Feb 10